

# Technical datasheet

## PLA Semi Matte

color**Fabb**

Date of issue: November 20<sup>th</sup>, 2023  
Version: v1.0

### Description

The colorFabb Semi Matte is a high quality PLA 3D printing filament, modified to withstand high impact and provide a matte finish to any printed object. The PLA Semi Matte is also available on 750 gram and 2200 gram spools in various colors.

### Typical Properties

#### Mechanical Properties – 3D Printed

	Method	Value		Unit
		XY	Z	
Youngs Modulus	Tensile, ISO 527-1A	3300	3350	MPa
Tensile Strength	Tensile, ISO 527-1A	70	71	MPa
Elongation at break	Tensile, ISO 527-1A	3,5	3,5	%
Flexural Modulus	Flexural, ISO 178	2400	2200	MPa
Flexural Strength	Flexural, ISO 178	97	85	MPa
Impact Strength	Charpy Notch, ISO 179	4.0	N/A	kJ/m <sup>2</sup>

#### Mechanical Properties – Injection Molded\*

	Method	Value	Unit
Youngs Modulus	Tensile, ISO 527-1A	3500	MPa
Tensile Strength	Tensile, ISO 527-1A	45	MPa
Elongation at break	Tensile, ISO 527-1A	≤5.0	%
Flexural Strength	Flexural, ISO 178	N/A	MPa
Charpy Impact Strength	Charpy Notch, ISO 179	≤5.0	kJ/m <sup>2</sup>
Density	ISO 1183	1,2	g/cm <sup>3</sup>

#### Thermal Properties

	Method	Value	Unit
Glass Transition Temp.	DSC, ISO 11357	55-60	°C
Melting Temp.	DSC, ISO 11357	150-160	°C
Decomposition Temp.	TGA, ISO 11358	N/A	°C
Heat Deflection Temp.	HDT-B, ISO 75	60	°C
Melt Flow Index	MFI, (210°C/2.16 kg), ISO 1133-A	6	g/10min
Melt Flow Index	MFI, (190°C/1.16 kg), ISO 1133-A	3	g/10 min

\*These results are obtained from the information provided by the supplier of the raw material

# Technical datasheet

## PLA Semi Matte

color**Fabb**

Date of issue: November 20<sup>th</sup>, 2023  
Version: v1.0

### Filament Specifications

	Unit		
Diameter	mm	1.75	2.85
Max. roundness deviation	mm	± 0.05	± 0.1
Ovality	%	≥95	≥95
Net. Filament weight	g	750/2200	750/2200

### Guideline for print settings

	Unit	
Nozzle Temp.	°C	195-220
Bed Temp.	°C	50-60
Bed / surface modification	-	Tape or Glue
Active cooling fan	%	100
Print Speed	mm/s	40-100

### Notes

The reported properties are an average of a batch of 3D specimens.

The specimens have been printed in XY and Z plane, using 0.15 mm layer height, 100% infill, 0,4 mm nozzle, 210 °C nozzle temperature, and 55°C bed temperature.

### Disclaimer

The product- and technical information provided in this datasheet is correct to the best of our knowledge. The information given is provided as a guidance for good use, handling and processing, and is not to be considered as a quality specification. The information only relates to the specific product and the material properties.